



Technical Specifications RGD-40655

Properties	Value	Standard
Dimensions		
Thickness	55± 10% mm	
Width (of rolls)	1 ± 10% m	
Length (of rolls)	Any m	
Density	30 ± 10% kg/m ³	
REACH	Pass	Regulation(EC) No.1907/2006 + (EC) No 1272/2008
Vertical water infiltration rate	>24000 mm/h	EN 12616:2013 Part 1 - Method A
CFH Value (Test Base Concrete)		
55mm Shockpad+35mm grass+25kgs/m ² sand	3.08 m	EN 1177:2008
55mm Shockpad+35mm grass+10kgs/m ² sand	2.70 m	EN 1177:2008
55mm Shockpad+15mm grass+6kgs/m ² sand	2.30 m	EN 1177:2008
Migration of certain elements	Pass	EN71-3:2013+A1:2014

All specifications are based on reports of independent laboratories and the knowledge of Regalfill at the time of printing .
Regalfill Reserves the right of changing the specifications and/or the products .