

PERFORMANCE REPORT

CUSTOMER: Zeodorizer Llc **DATE SAMPLED:** 05/01/2018
PROJECT: Ammonia Absorption

Performance Data

	Zeodorizer	Mineral Absorbent (baseline)
Initial	~50% eliminated	~10% eliminated
30 mins later	~85% eliminated	~30% eliminated

Physical Data

**Moisture Holding
Capacity**

100.53% by
weight

Color

Beige/Tan

Chemical Data: (TBD)

SiO₂ Al₂O₃ Fe₂O₃ CaO MgO Na₂O K₂O MnO TiO₂

PREPARED BY: Adam Williamson

Adam Williamson
Geochemist